



Registration Certificate

Carpet Name: **MUNICH 180Z SDN SERIES**

Licensee: **ARTISTIC FLOORING**

Licence Number: **1801**

Label Number: **20138**

ACCS Contract Grading: **CEHD 4***

ACCS Residential Grading: **REHD2 6***

Suitable for Stairs: **Yes**

Date Printed: **13/10/2020**



Allan Firth



Allan Firth
Secretary ACCS



Administered by the Carpet Institute of Australia Limited ABN 11 006 829 303

PO Box 7172, St Kilda Road, Melbourne Victoria 8004 Tel: (03) 9804 5559 • Fax: (03) 9804 5560

Email: info@carpetoz.com.au • www.carpetinstitute.com.au

This certificate remains the property of the Carpet Institute of Australia Limited.

Carpet Details:

Company: ARTISTIC FLOORING

Label No: 20138

Licence No: 1801

Office No: 7056

Names:

MUNICH 18OZ SDN SERIES

Details:

Awarded Res Grade: REHD2 6*
 Awarded Con Grade: CEHD 4*
 Registered On: 13/10/2020
 Active: Yes
 Date In-Active:
 Manufacture Method: Tufted
 Twist Set: N/A
 Dyeing Method: Melt Dyed
 #Colours/Designs: 5/6
 Backing Type: Other
 Felted: N/A
 Spinning System: BCF
 Insect Resist Agent: N/A
 Filament: /
 Master Product: 18100

Test Results:

Pile Mass g/m² (oz/yd²): 610 (18.0)
 SPM g/m² (oz/yd²): 404 (11.9)
 Stated Pile Height (mm): 4.0
 Minimum Pile Height (mm): 3.0
 Maximum Pile Height (mm): 4.5
 Dynamic Loading Loss (%): 0.0
 Static Loading Loss (%): 0.0
 Tex (g/1000m): 320
 Measured Pile Thickness (mm): 3.0
 Machine Gauge (Tufts/dm): 50.4
 Meas Tufts Perp to Selvedge: 47.5
 Meas Tufts Para to Selvedge: 40.1
 Treated For Soiling Resistance: No
 Soil Resist Inhibitor: No
 Stain Resist Inhibitor: No

Hexapod Scores:

	Texture		Colour		Thickness	
	WA	WA	WA	WA	(mm)	(%)
1500:	4.5	4.5	4.5	4.5	0.3	11.5
8000:	3.0	3.0	4.0	4.0	1.0	34.7

Quality Assurance Test:

Cut Pile (%): 0
 Loop Pile (%): 100
 Panel Assessment Contract: 14
 Panel Assessment Residential: 14
 Suitable For Stairs: Yes
 Tile: Yes SheetGoods: No
 Fibre Signature: NBA:100

ACCS Test:

	Con	Res	Max
SPM/PH Ratio:	16	16	16
Volume Density:	17.2	17.2	20
Tuft Density:	9	9	9
Dyn Load:	3.9	3.9	5
Stat Load:	4.1	4.1	5
Soiling Prop:	12	12	16
Abrasion Res:	10	10	10
Sub Total:	72.2	72.2	81
Panel Assess:	14	14	19
Total:	86.2	86.2	100
Calc Residential Grade:	REHD2		6*
Calc Contract Grade:	CHD		3*

Calculations

Pile Height(mm): 3.1
 Tuft Density(per dm²): 1904.8
 GSPM(g/m²): 390.0
 GSPM (abrasive) (g/m²): 275.0
 Soiling Propensity: 12.0 +0.0

OAF Values

OAF: 4.2
 Calc Density (+-5%): 0.13 0.135 0.14
 Base Fibre: NYLON
 Benchmarks:
 RHD1 0 RHD2 3.5
 REHD1 3.5 REHD2 3.5

Environmental Classification:

ECS:

Level: 0

	Calc	B/M	P/F
Acoustic:	3	3	PASS
Thermal:	22.3	15	PASS
VOC:			
TVOC	0		

Notes:

13/10/2020 - Cloned From Master - (18100) by D Williams.